



Product data
Floorify® Performance Underlay
Underlay for Floorify® Rigid Vinyl Planks & Tiles

Version:








01/05/2023 (EN)

Size and basic information

Floorify® Performance Underlay is especially designed to be used in combination with Floorify® Rigid Vinyl Planks & Tiles and exceeds on all parameters the minimum requirements on underlayments. Floorify® Performance Underlay is manufactured without CFCs and HFCCs and contains neither plasticizers nor heavy metals or other hazardous substances.

m ² /roll:	10	m ²
length	10	m
width	1	m
thickness	EN823 1,5	mm
qty/pallet	40	rolls 400 m ²

Technische data

			Norm Requirements	Floorify® results
	Impact sound improvement	ISO 10140 / ISO717-2	ΔLw18Db	In combination with Floorify® Rigid Vinyl Planks & Tiles: ΔLw16Db
	Compressive strength	EN826	≥ 10kPa (MMFA)	≥ 450 kPa
	Compressive creep	EN1606	≥ 2kPa	87 kPa
	Castor chair test	ISO 4918	>25000 rotaties, non delminiation, no visible changes	Tested in combination with Floorify® Rigid Vinyl Planks & Tiles: pass
	Impact resistance:	EN13329	≥ 1 200 mm	In combination with Floorify® Rigid Vinyl Planks & Tiles: 1800mm - IC3
	Fire classification:	EN 13501-1 EN ISO 11925-2		Efl
	Thermal resistance (floor + underlay)	EN12667	<0,15R (m ² K/W)	0,0213 R24 (m ² K/W) (Floorify® in combination with Floorify® Performance underlay) Underlay only: 0,0093 R24 (m ² K/W)
	Floor heating:		appropriate for all standard heating systems IN cement flooring. NOT appropriate for heating films.	
	CE:	EN 14041	DoP FF004	

Floorify NV reserves the right to make alterations to material and structures when this serves to improve the quality

Floorify NV, Kruisboommolenstraat 30A 8800 ROESELARE, BELGIUM - Email: sales@floorify.com -T+32 475 760351 of +32 473 65 18 21