



Product data
Floorify® Rigid Vinyl Planks & Tiles
 click

version: 30/09/2026

EN

Dimensions and basic data						
				Small tiles	Planks	Long Planks
		Width	ISO24342	305	178	225
		Length	ISO24342	610	1219	1524
						mm
		Number of panels per pack	-	12	12	8
						pc
		m² per pack	-	2,23	2,6	2,74
						m²
		Weight per pack	ISO23997	17,42	19,9	20
						kg
		Total thickness	ISO24346	4	4	4
						mm
		Top Layer thickness	ISO24340	0,55	0,55	0,55
						mm
	Core	-	Sound reducing, robust and waterproof Floorify® Rigid Core			
	Finish	-	Protected with stain resistant Floorify® Quiet Sense Technology			
	Locking method	-	Traditional glueless click under license of Unilin.			
Warranty						
	Usage class	ISO10582	33			
	CE	EN 14041	DoP FF001			
	Warranty	Residential / Commercial	Residential: 25 years (Lifetime when installed on Floorify® Performance underlay) Commercial: 5 years only when installed on Floorify® Performance underlay			
Technical data						
		Norm	Norm Requirements			Floorify values
	Wear resistance	ISO24338, Procedure A	≥ 2000 cycles			≥ 4000 cycles - AC4
	Impact resistance	EN13329	≥ 1600 mm			In combination with Floorify underlays: 1800mm - IC3
	Residual indentation	ISO24343-1	≤ 0,2 mm			In combination with Floorify underlays: no visible changes
	Stain resistance	EN438-2	Groups 1 and 2: grade 5; Group 3: grade 4			Groups 1, 2 and 3: grade 5;
	UV resistance	ISO 105-B02:2014, Method 3	≥ 6			> 6
	Fire classification	EN 13501-1 ISO 9239-1				Bfl-s1
	Dimensional stability	EN ISO23999 6uur bij 80C	≤ 0,15 % Curling ≤ 2mm			≤ 0,10 % OK
	Locking strength	ISO24334	Long side: ≥ 1kN/m Short side: ≥ 1,5kN/m			Long side: > 4,5kN/m Short side: > 4,5kN/m

	Displacement of furniture feet	EN ISO16581	Foot 0,1mm / 32kg		No changes
	Castor chairs	EN ISO4918	≥ 25000 cycles: No delamination, no disturbance		In combination with Floorify underlays: no visible changes
	Slip resistance	EN13893 EN 16165	-		DS R10
	Thermal resistance (floor + underlay)	EN12667	< 0,15R (m²K/W)		0.0213 R24 (m²K/W) (0.0120 floor + 0.0093 Performance Underlay) 0.0660 R24 (m²K/W) (0.0120 floor + 0.0540 Comfort Underlay)
	Floor heating	Appropriate for all standard heating systems IN cement flooring. NOT appropriate or tested with heating films.			
	Impact sound improvement	ISO 10140 / ISO717-2	ΔLw18dB		In combination with Floorify® Comfort underlay: ΔLw20dB (ΔLin10dB)
Dangerous Substances					
	Formaldehyde emission	EN14041 / EN717-1	E1		
	TVOC 28 days	< 1000µg/m³	< 10µg/m³		
	Emissions in the interior air	Decree n° 2011-321	A+		
	REACH	-	Floorify® floors and accessories are fully REACH compliant		
	Plasticizers	-	DOTP - virgin PVC - 100% orthophtalate free		

Floorify NV reserves the right to make alterations to material and structures when this serves to improve the quality
Floorify NV, Kwadestraat 151, 8800 Roeselare, BELGIUM - Email: hello@Floorify.com - T+32 (0)51 140 180