

Glaze Agate

kettal

Description

An exclusive paint finish that replicates the aesthetic qualities and feeling of warmth offered by ceramics. As a result of its technical properties, Glaze also delivers the same level of durability and quality provided by aluminium coatings.

Colors



Botswana
392



Carnelian
390



Indian
391



Moss
393



Sapphire
394

Technical specifications

| Characteristics | Paint | Lacquer | Method |
|---------------------------|-------------|-------------|------------|
| Baking time / temperature | 25 at 150°C | 15 at 190°C | Total time |
| Thickness of the film | 110 | 110 | ISO 2360 |
| Gloss at 60° angle | 69 | 40 | ISO 2813 |
| Direct impact 15.9 mm | 30 | 50 | ISO 6272 |
| Indirect impact 15.9 mm | 30 | 50 | ISO 6272 |
| Cross-cut adhesion | 0 | 0 | ISO 2409 |
| Erichsen Cupping test | 7 | 10 | ISO 1520 |
| Bending test | 6 | 5 | ISO 1519 |
| Avg. Particle size | 62,05 | 52,72 | MALVERN |

