

Lime

TRADIBAT 85[®]



TECHNICAL FEATURES

- **NORMATIVE NAME:** HL 5 CE
- **COLOR:** Grey
- **SETTING TIME:** 3h30
- **RESISTANCE:**

at 28 days	11 MPa
------------	--------
- **GREY CEMENT CONTENT:** approx. 20%
- **ADDITIVES:** plasticity agents



GRAY LIME formulated for all your applications

PRODUCT BENEFITS



STRENGTH AND REACTIVITY

- Very short initial setting time, allowing joints applied in the morning to be finished the same day
- Tradibat 85[®] suitable for new supports and hard old supports

GREY COLOR

- Formulated with hydraulic lime, grey cement, and plasticity agents
- Gray lime for coloring your renders

FORMULATED FOR ALL APPLICATIONS

- Usable in spray pots (sablon)
- Versatile: suitable for masonry, rendering, and roofing

COMMERCIAL SHEET: **TRADIBAT 85®**

USES

RENDERS ON NEW OR HARD SUPPORTS

- Manual renders
- Machine-applied renders (spray pot / sablon)
- Decorative exterior renders
- Base coat renders

MASONRY AND ROOFING

- Filling bricks, blocks, and stones
- Masonry with stones and facing bricks
- Pointing of stones and bricks
- Flashings, ridges
- Masonry of tiles

LIME-HEMP WORKS

- Hempcrete for floors, walls, and roofs
- Installation carried out by certified applicators in accordance with professional standards



CREAMY MORTAR













STONE MASONRY



MASONRY OF TILES

DOSAGES



	Lime (bucket)	Sand type (bucket) 0/2 mm - 0/4 mm	Equivalent dosage Kg of lime / m ³ of sand
EXTERIOR RENDER – BASE COAT	 1	 2	350 - 450 kg/m ³
EXTERIOR RENDER – FINISH COAT	 1	 3	250 - 400 kg/m ³
MASONRY WITH HARD STONE	 1	 2	300 - 400 kg/m ³
MASONRY WITH FIRM STONE	 1	 3	200 - 400 kg/m ³
INSTALLATION OF SEALED FLOOR COVERINGS	 1	 2,5	250 - 350 kg/m ³

Dosages and particle sizes are provided for informational purposes only and may vary depending on the source of the materials, their water content and the local technical standards.

The technical specifications and restrictive conditions of use of our products are available upon request with FTP.

EXCLUSIVE SERVICES

Safety:

clear safety and ergonomic recommendations printed on all bags.

Website:

general info, data and commercial sheets, safety data, and performance declarations...

www.lafarge.fr 

Lafarge Ciments Distribution

14-16 boulevard Garibaldi
92130 Issy-les-Moulineaux