

Lime

TRADIFARGE® PLUS

25Kg



TECHNICAL FEATURES

- **NORMATIVE NAME:** HL 5 CE
- **COLOR BRIGHTNESS L*:** 92
- **SETTING TIME:** 3h30
- **RESISTANCE:**

at 28 days	12 MPa
------------	--------
- **WHITE CEMENT CONTENT:** 25%
- **ADDITIVES:** smoothness agents



White LIME Formulated for all your applications

PRODUCT BENEFITS



STRENGTH

- One of the most resistant limes on the market thanks to the addition of white cement (25%).
- Tradifarge® Plus is suitable for new and hard supports

SPECIFIC FORMULATION

- Its high whiteness (L* 92) allows the mortar to reproduce the natural color of sands
- Suitable for all applications, Tradifarge® Plus gives your mortars exceptional smoothness
- Specially formulated for use with spray machines.

REACTIVITY

- Tradifarge® Plus has a shorter setting time than other limes in the range
- Allows for the laying of stones and blocks thanks to a more reactive mortar

COMMERCIAL SHEET: **TRADIFARGE® PLUS**

USES

RENTERS ON NEW OR HARD SUBSTRATES

- Manual renders
- Machine-applied renders (projection pot / sprayer)
- Decorative exterior renders
- Base coat renders

MASONRY AND JOINTING

- Laying of bricks, blocks, and stones
- Masonry for facing bricks and stones
- Pointing of bricks and stones

SOIL COVERING AND STABILIZATION

- Flashings, ridges
- Tile masonry
- Soil stabilization



TERRACOTTA FLOOR













MACHINE APPLICATION



COATING

DOSAGES

 25Kg

	Lime (bucket)	Sand type (bucket) 0/2 mm - 0/4 mm	Equivalent dosage Kg of lime / m ³ of sand
EXTERIOR RENDER COAT - BASE COAT	 1	 2	350 - 450 kg/m ³
EXTERIOR RENDER COAT - FINISH	 1	 3	250 - 400 kg/m ³
MASONRY - HARD STONE	 1	 2	300 - 400 kg/m ³
MASONRY - MEDIUM-HARD STONE	 1	 3	200 - 400 kg/m ³
TERRACOTTA TILE SETTING	 1	 2,5	250 - 350 kg/m ³

Dosages and particle sizes are provided for informational purposes only and may vary depending on the source of the materials, their water content and the local technical standards.

The technical specifications and restrictive conditions of use of our products are available upon request with FTP.

EXCLUSIVE SERVICES

Safety:

clear safety and ergonomic recommendations printed on all bags.

Website:

general info, data and commercial sheets, safety data, and performance declarations...

www.lafarge.fr 

Lafarge Ciments Distribution

14-16 boulevard Garibaldi
92130 Issy-les-Moulineaux