

TECHNICAL SPECIFICATION

ARTICLE 0377

ARTICLE DESCRIPTION

THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	15 ± 1 yarns / dm (leno)
	Weft	8 ± 1 yarns / dm
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 13,3 x 12,5 mm
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	377 g/m² ± 5 %

MAIN FEATURES

COMPOSITION	Fiberglass		100 %
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)	Warp	Breaking strength Average value 4000 N/5 cm	Elongation 3,0 % ± 1
	Weft	Average value 4600 N/5 cm	3,0 % ± 1

NOTES

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its date should be reported on the order.

Version 1 of

28/01/2022

TECHNICAL MNG.

