

AZIENDA CON SISTEMA
DI GESTIONE QUALITÀ
CERTIFICATO DA DNV GL
= ISO 9001 =

OGGETTO DELLA CERTIFICAZIONE: Sviluppo, produzione e commercializzazione di tessuti tecnici in fibra di vetro e in altre fibre COMPANY WITH
QUALITY SYSTEM
CERTIFIED BY DNV GL
= ISO 9001 =

OBJECT OF CERTIFICATION:

Development, manufacture and trade of technical fabrics made of fiberglass and of other fibers

## **TECHNICAL SPECIFICATION**

## **ARTICLE 0060T07**

ARTICLE DESCRIPTION				
THREADS SP 04/02/10	Warp	48,8 ± 1 yarns / dm		
(UNI EN 1049-2)	Weft	38 ± 1 yarns / dm		
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 2 x 2,6 mm		
<b>WEIGHT</b> SP 04/02/12 (ISO 3374)	Raw mesh	59 g/m² ± 6%		
	Finished mesh	82 g/m² ± 6%		
	MAIN FEATURE	S		
ATN ADDITION (C)				

MAIN APPLICATION (5)	Heat-rastening scrim for hot-temperature coupling		
COMPOSITION	Fiberglass		approx. 72 %
COMPOSITION	Heat-fastening glue (Eva Ethylene Vinyl Acetate)		approx. 28 %
RESISTANCE TO TENSILE STRENGTH		Breaking strength	Elongation

RESISTANCE TO TENSILE		Breaking s
STRENGTH	Warp	Average value 1
SP 04/02/13 (ISO 4606)		
(150 4606)	Weft	Average value

	Breaking strength	Elongation
Warp	Average value 1000 N/5 cm	4,0 % ± 1
Weft	Average value 750 N/5 cm	4,0 % ± 1

## STORAGE

Store the material at a temperature < 50° C (122° F) in the original packaging protecting it from atmospheric agents.

Usage is recommended within 12 months from delivery date.

## NOTES

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its version date should be reported on the order.

Versione 1 del 12/09/2022

TECHNICAL MNG.

