



Sede centrale / Headquarter
Via Gavazzi, 3
23801 Calolziocorte (LC), Italia
Tel. +39 0341 641051 | Fax +39 0341 633004
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001-ISO 50001

GAVAZZI TESSUTI TECNICI S.p.A. s.u.

TECHNICAL SPECIFICATION

ARTICLE B0130-A

ARTICLE DESCRIPTION

THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	16 ± 1 yarns/dm (leno)
	Weft	4 ± 0,5 yarns / dm
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 25 x 25 mm
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	112 g/m ² ± 10 %
	Finished mesh	137 g/m ² ± 10 %

MAIN FEATURES

COMPOSITION	Fiber Basalt	approx. 82 %	
	Alkali resistant finish	approx. 18 %	
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)		Breaking strength	Elongation
	Warp	Average value 40 kN/m	5,5 % ± 1
	Weft	Average value 30 kN/m	4,5 % ± 1

NOTES

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical sheet version in the hands of the customer is updated, its version should be reported on the order.

Version 0 of 13/06/2023

TECHNICAL MNG *Signed on original copy*

