




Sede centrale / Headquarter
 Via Gavazzi, 3
 23801 Calolziocorte (LO), Italia
 Tel. +39 0341 641051 | Fax +39 0341 633004
 info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
 QUALITY SYSTEM
 CERTIFIED BY DNV
 ISO 9001

GAVAZZI TESSUTI TECNICI S.p.A. s.u.



TECHNICAL SPECIFICATION		ARTICLE 0650AP01	
ARTICLE DESCRIPTION			
THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	50 ± 1 yarns / dm	
	Weft	39 ± 1 yarns / dm	
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	650 g/m ² ± 8 %	
	Finished mesh	735 g/m ² ± 8 %	
MAIN FEATURES			
COMPOSITION	Fiberglass		88 %
	Finish		12 %
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)		Breaking strength	Elongation
	Warp	Average value 7700 N/5 cm	4,0 % ± 1
	Weft	Average value 5300 N/5 cm	8,0 % ± 3
NOTES			
<p>Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.</p>			
<p>Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its date should be reported on the order.</p>			
Version 0 of 02/05/2023		TECHNICAL MNG.	