



GAVAZZI TESSUTI TECNICI S.p.A. S.U.

Sede Centrale / Headquarter:
Via Gavazzi, 3 – 23801 Calolziocorte (LC) - ITALIA
Tel. +39 0341 641051 r.a. – Fax +39 0341 633004 / +39 0341 644823
E-mail: info@gavazzispa.it – www.gavazzispa.it

AZIENDA CON SISTEMA
DI GESTIONE QUALITÀ
CERTIFICATO DA DNV GL
= ISO 9001 =

Oggetto della Certificazione:
Sviluppo, produzione e commercializzazione
di tessuti tecnici in fibra di vetro e in altre fibre.

TECHNICAL SPECIFICATION		ARTICLE 0078T07	
ARTICLE DESCRIPTION			
THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	32 ± 1 yarns / dm	
	Weft	22,5 ± 1 yarns / dm	
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 3,1 x 4,4 mm	
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	52 g/m ² ± 6 %	
	Finished mesh	76 g/m ² ± 6 %	
MAIN FEATURES			
MAIN APPLICATION (S)	Heat-fastening scrim for hot-temperature coupling		
COMPOSITION	Fiberglass		approx. 68 %
	Heat-fastening glue		approx. 32 %
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)	Breaking strength		Elongation
	Warp	Average value 600 N/5 cm	4,0 % ± 1
	Weft	Average value 800 N/5 cm	4,0 % ± 1
STORAGE			
Store the material at a temperature < 50° C (122° F) in the original packaging, protecting it from atmospheric agents. Usage is recommended within 12 months from delivery date.			
NOTES			
Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.			
Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its version date should be reported on the order.			
Version 1 of 12/09/2022		TECHNICAL MNG. Signed on original copy	

Sede legale / Registered Office: Viale Elvezia 12 - 20154 Milano- Italia / Cap.Soc. € 12.300.000 i.v. - Reg. Imp. (MI) / C.F. / P.I. IT 02672970130 – REA MI 1892085

Uff. Comm. Italia/Italy Sales Office:
20154 Milano
Viale Elvezia, 12
Tel + 39 02 313345
Fax + 39 02 34535822

Polo Logistico/Main Warehouse:
23801 Calolziocorte (LC)
Via Alcide De Gasperi
Tel + 39 0341 634466
Fax + 39 0341 631700

Stabilimenti Produttivi/Production Plants:
24034 Cisano Bergamasco (BG) 20862 Arcore (MB)
Via delle industrie 3 Via Monte Cervino 66
Tel + 39 035 4364072 Tel + 39 039 6014474
Fax + 39 035 4381913 Fax + 39 039 6015622