



GAVAZZI TESSUTI TECNICI S.p.A. s.u.

Sede centrale / Headquarter
Via Gavazzi, 3
23801 Calolziocorte (LC), Italia
Tel. +39 0341 641051 | Fax +39 0341 633004
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001•ISO 50001

TECHNICAL SPECIFICATION		GAVADES	
Water-based adhesive for fiberglass wall-coverings GAVATEX			
ARTICLE DESCRIPTION			
CONSISTENCY	Creamy paste		
COLOUR	White	DRY SOLID CONTENT	23 %
DENSITY	1,04 g/cm ³	pH	8,5
BROOKFIELD VISCOSITY	100 mPa . s	6 Rotor – rpm 5	
STORAGE	Avoid storing for a long period at temperature under 0° C .		
INFLAMMABILITY	no	HEALTH AZARD	no
APPLICATION DATA AT +23°C AND 50% R.H.			
APPLICATION TEMPERATURE RANGE		From + 10°C to + 35°C	
TIME	WAITING	From 0 to 10 minutes	
	OPEN	Maximum 30 minutes	
	SETTING	Approx. 6-8 hours	
	FINAL SETTING	Approx. 48 hours	
FINAL PERFORMANCE DATA			
RESISTANCE TO	AGEING	Excellent	
	TEMPERATURE	Max +80°C	
	DAMP	Good	
	MOULD	Good	
CONSUMPTION	Depends on the surface on which it is applied , approx. consider 300-400 g/m ²		
STANDARD PACKAGING			
1 palet 80/120/120 cm contains 24 buckets i.e. 480 kg net			
NOTES			
Above data are based on our experience. They are liable to amendments and should be verified by the custode in case of special use. In order to verify that the tecnica data sheet in the hands of the custode is updated. Its version should be reported on the order.			
Version 1 of 24/06/2024		TECHNICAL MNG Signed on original copy	

Sede legale / Registered Office: Via Melzi d'Eril, 3 - 20154 Milano - Italia | Cap.Soc. € 12.300.000 i.v. | Reg. Imp. (MI) | C.F. / P.I. IT 02672970130 | REA MI 1892085

Uff. Comm. Italia / Italy Sales Office:
Via Melzi d'Eril, 3
20154 Milano
Tel. +39 02 313345

Polo Logistico / Main Warehouse:
Via Antonio Stoppani, 20
23801 Calolziocorte (LC)
Tel. +39 0341 634466

Stabilimenti Produttivi / Production Plants:
Via delle Industrie, 3
24034 Cisano Bergamasco (BG)
Tel. +39 035 4364072

Via Monte Cervino, 66
20862 Arcore (MB)
Tel. +39 039 6014474