

GAVAZZI

Sede centrale / Headquarter
Via Gavazzi, 3
23801 Calolziocorte (LC), Italia
Tel. +39 0341 641051 | Fax +39 0341 633004
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001•ISO 50001

GAVAZZI TESSUTI TECNICI S.p.A. s.u.

TECHNICAL SPECIFICATION

ARTICLE 0074A78

ARTICLE DESCRIPTION

THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	50 ± 1 yarns / dm (leno)
	Weft	12 ± 1 yarns / dm
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 4 x 8,3 mm
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	58 g/m² ± 5 %
	Finished mesh	71 g/m² ± 5 %

MAIN FEATURES

COMPOSITION	Fiberglass		approx. 82 %
	Alkali resistant finish		approx. 18 %
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)	Warp	Breaking strength	Elongation
		Average value 1300 N/5 cm	4,5 % ± 1
	Weft	Average value 900 N/5 cm	4,5 % ± 1

NOTES

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its version date should be reported on the order.

Version 0 of 09/11/2022

TECHNICAL MNG. Signed on original copy