



Sede centrale / Headquarter
 Via Gavazzi, 3
 23801 Calolziocorte (LC), Italia
 Tel. +39 0341 641051 | Fax +39 0341 633004
 info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
 MANAGEMENT SYSTEM
 CERTIFIED BY DNV
 ISO 9001-ISO 50001

GAVAZZI TESSUTI TECNICI S.p.A. s.u.

TECHNICAL SPECIFICATION		ARTICLE 0075-A	
ARTICLE DESCRIPTION			
THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	50 ± 1 yarns / dm (leno)	
	Weft	20 ± 1 yarns / dm	
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 4 x 5 mm	
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	75 g/m ² ± 5%	
	Finished mesh	90 g/m ² ± 5%	
MAIN FEATURES			
MAIN APPLICATION (S)	Wall plaster reinforcement Reinforcement of marble slabs with polyester or epoxy resins Mounting of tiles and mosaics with cold and "hot-melt" resins		
COMPOSITION	Fiberglass	approx. 84 %	
	Alkali resistant finish	approx. 16 %	
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)	Breaking strength		Elongation
	Warp	Average value 1450 N/5 cm	4,5 % ± 1
	Weft	Average value 1550 N/5 cm	4,5 % ± 1
STANDARD PACKAGING			
Mesh width 1000 ; 1200 ; 1300 ; 1400 ; 1500 ; 1600 ; 1800 ; 2000 mm - roll length 100 ; 300 m - on cardboard core and in polythene			
NOTES			
Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.			
Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its date should be reported on the order.			
UPDATED 07/01/2009		PLANT MNG. Signed on original copy	

