

**GAVAZZI**

Sede centrale / Headquarter  
 Via Gavazzi, 3  
 23801 Calolziocorte (LO), Italia  
 Tel. +39 0341 641051 | Fax +39 0341 633004  
 info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH  
 MANAGEMENT SYSTEM  
 CERTIFIED BY DNV  
 ISO 9001-ISO 50001

GAVAZZI TESSUTI TECNICI S.p.A. s.u.

**TECHNICAL SPECIFICATION****ARTICLE 0159R****ARTICLE DESCRIPTION**

<b>THREADS</b> SP 04/02/10 (UNI EN 1049-2)	Warp	28 ± 1 yarns / dm (leno)
	Weft	13,5 ± 1 yarns / dm
<b>MESH WIDTH</b> SP 04/02/11	Measured between yarn midpoints	approx. 7,1 x 7,7 mm
<b>WEIGHT</b> SP 04/02/12 (ISO 3374)	Raw mesh	122 g/m <sup>2</sup> ± 5 %

**MAIN FEATURES**

<b>COMPOSITION</b>	Fiberglass		approx. 100 %
<b>RESISTANCE TO TENSILE STRENGTH</b> SP 04/02/13 (ISO 4606)	<b>Breaking strength</b>		<b>Elongation</b>
	Warp	Average value 1380 N/5 cm	3,5 % ± 1
	Weft	Average value 1750 N/5 cm	3,5 % ± 1

**STANDARD PACKAGING**

Mesh width 1000 mm - roll length to be defined - on cardboard core and in polythene

**NOTES**

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its version should be reported on the order.

**Version 2 of 19/09/2024****TECHNICAL MNG.** Signed on original copy