



GAVAZZI TESSUTI TECNICI S.p.A. s.u.

Sede centrale / Headquarter
Via Gavazzi, 3
23801 Calolziocorte (LC), Italia
Tel. +39 0341 641051 | Fax +39 0341 633004
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001-ISO 50001

TECHNICAL SPECIFICATION

ARTICLE 0073-A

ARTICLE DESCRIPTION

THREADS SP 04/02/10 (UNI EN ISO 7211-2)	Warp	50 ± 1 yarns / dm (leno)
	Weft	20 ± 1 yarns / dm
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 4 x 5 mm
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	61 g/m ² ± 5 %
	Finished mesh	74 g/m ² ± 5 %

MAIN FEATURES

MAIN APPLICATION (S)	Wall plaster reinforcement. Reinforcement of marble slabs with polyester or epoxy resins. Mounting of tiles and mosaics with cold and "hot-melt" resins.		
COMPOSITION	Fiberglass		approx. 82 %
	Alkali resistant finish		approx. 18 %
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)		Breaking strength	Elongation
	Warp	Average value 1300 N/5 cm	4,5 % ± 1
	Weft	Average value 1000 N/5 cm	4,5 % ± 1

STANDARD PACKAGING

Mesh width 1000; 1200; 1300; 1400; 1500; 1600; 1800; 1900; 2000 mm - roll length 100 ; 300 m -
on cardboard core and in polythene

NOTES

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its date of version should be reported on the order.

Version 2 of 24/04/2025

TECHNICAL MNG. Signed on original copy