



GAVAZZI TESSUTI TECNICI S.p.A. s.u.

Sede centrale / Headquarter
Via Gavazzi, 3
23801 Calolziocorte (LC), Italia
Tel. +39 0341 641051 | Fax +39 0341 633004
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001-ISO 50001

TECHNICAL SPECIFICATION		ARTICLE 0109-A	
ARTICLE DESCRIPTION			
THREADS SP 04/02/10 (UNI EN ISO 7211-2)	Warp	44 ± 1 yarns / dm (leno)	
	Weft	16 ± 1 yarns / dm	
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	100 g/m² ± 5%	
	Finished mesh	128 g/m² ± 5%	
MAIN FEATURES			
MAIN APPLICATION (S)	Mosaics and ceramic tiles assembly with vinyl glue.		
COMPOSITION	Fiberglass		approx. 78 %
	Alkali resistant finish		approx. 22 %
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)	Warp	Breaking strength	Elongation
		Average value 2300 N/5 cm	4,5 % ± 1
	Weft	Average value 800 N/5 cm	3,5 % ± 1
		STANDARD PACKAGING	
Mesh width by request - roll length from 100 to 400 m – on cardboard core and in polythene			
NOTES			
Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.			
Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its version should be reported on the order.			
Version 1 of 20/05/2025		TECHNICAL MNG. Signed on original copy	

