



GAVAZZI TESSUTI TECNICI S.p.A. s.u.

Sede centrale / Headquarter  
Via Gavazzi, 3  
23801 Calolziocorte (LO), Italia  
Tel. +39 0341 641051 | Fax +39 0341 633004  
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH  
MANAGEMENT SYSTEM  
CERTIFIED BY DNV  
ISO 9001-ISO 50001

## TECHNICAL SPECIFICATION

ARTICLE 0073T07

### ARTICLE DESCRIPTION

<b>THREADS</b> SP 04/02/10 (UNI EN ISO 7211-2)	Warp	50 ± 1 yarns / dm (leno)
	Weft	20 ± 1 yarns / dm
<b>MESH WIDTH</b> SP 04/02/11	Measured between yarn midpoints	approx. 4 x 5 mm
<b>WEIGHT</b> SP 04/02/12 (ISO 3374)	Raw mesh	61 g/m <sup>2</sup> ± 6 %
	Finished mesh	81 g/m <sup>2</sup> ± 6 %

### MAIN FEATURES

<b>MAIN APPLICATION (S)</b>	Heat-fastening scrim for hot-temperature coupling	
<b>COMPOSITION</b>	Fiberglass	approx. 75 %
	Heat-fastening glue (Eva Ethylene Vinyl Acetate)	approx. 25 %

### STORAGE

Store the material at a temperature < 50° C (122° F) in the original packaging, protecting it from atmospheric agents.  
Usage is recommended within 12 months from delivery date.

### NOTES

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its version should be reported on the order.

Version 2 of 27/05/2025

TECHNICAL MNG. Signed on original copy

