



Sede centrale / Headquarter
Via Gavazzi, 3
23801 Calolziocorte (LO), Italia
Tel. +39 0341 641051 | Fax +39 0341 633004
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001·ISO 50001

GAVAZZI TESSUTI TECNICI S.p.A. s.u.

TECHNICAL SPECIFICATION		ARTICLE 0060T19	
ARTICLE DESCRIPTION			
THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	48,8 ± 1 yarns / dm	
	Weft	38 ± 1 yarns / dm	
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 2 x 2,6 mm	
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	59 g/m ² ± 6 %	
	Finished mesh	79 g/m ² ± 6 %	
MAIN FEATURES			
MAIN APPLICATION (S)	Heat-fastening scrim for hot-temperature coupling		
COMPOSITION	Fiberglass	approx. 75 %	
	Heat-fastening glue (Acrylic)	approx. 25 %	
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)		Breaking strength	Elongation
	Warp	Average value 1000 N/5 cm	4,0 % ± 1
	Weft	Average value 750 N/5 cm	4,0 % ± 1
STORAGE			
Store the material at a temperature < 50° C (122° F) in the original packaging protecting it from atmospheric agents. Usage is recommended within 12 months from delivery date.			
NOTES			
Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.			
Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its version should be reported on the order.			
Version 0 del 11/02/2025		TECHNICAL MNG. Signed on original copy	

